

Precise PLA

PLA (Polylactic Acid) is a cost-effective option for non-functional prototyping. Markforged Precise PLA is ideal for design iterations, fit checks, concept models, and visual-only parts that are not mechanically demanding.

Note: Continuous Fiber is not compatible with Markforged Precise PLA.

	Test (ASTM)	P-PLA
Tensile Modulus (GPa)	D638	2.3
Tensile Stress at Yield (MPa)	D638	31
Tensile Stress at Break (MPa)	D638	18
Tensile Strain at Break (%)	D638	27
Flexural Strength (MPa)	D790 ¹	43
Flexural Modulus (GPa)	D790 ¹	2.3
Heat Deflection Temperature (°C)	D648 B	52
Izod Impact - notched (J/m)	D256-10 A	62
Density (g/cm ³)	—	1.3



Precise PLA is available in eight different colors to create color-coded prototypes, tool holders, and keep out zones.

P-PLA Colors

	Black
	Gray
	Yellow
	Red
	Blue
	Orange
	Green
	White

¹Measured by a method similar to ASTM D790. Parts do not break before end of flexural test.

Dimensions and construction of test specimens:

- Tensile: ASTM D638 type I beams
- Flexural: 3-pt. Bending, 4.5 in (L) x 0.4 in (W) x 0.12 in (H)
- Heat-deflection temperature at 0.45 MPa, 66 psi (ASTM D648-07 Method B)

Test Specimens:

All data were provided by an accredited 3rd party test facility. These represent typical values.

Markforged test plaques are uniquely designed to maximize test performance. Plastic test plaques are printed with full infill. To learn more about specific testing conditions or to request test parts for internal testing, contact a Markforged representative. All customer parts should be tested in accordance to customer's specifications.

Part and material performance will vary by layout design, part design, specific load conditions, test conditions, build conditions, and the like. This representative data were tested, measured, or calculated using standard methods and are subject to change without notice. Markforged makes no warranties of any kind, express or implied, including, but not limited to, the warranties of merchantability, fitness for a particular use, or warranty against patent infringement; and assumes no liability in connection with the use of this information. The data listed here should not be used to establish design, quality control, or specification limits, and are not intended to substitute for your own testing to determine suitability for your particular application. Nothing in this sheet is to be construed as a license to operate under or a recommendation to infringe upon any intellectual property right.

