



xMODEL35 – Rigid resin with optimum combination of strength, stiffness and temperature resistance.

Typical Values		Norm
General Properties		
Appearance	Available in Black, Gray	-
Viscosity, 30 °C	630 mPa	Cone/Plate Rheometer ¹
Yield Strength	160 mPa	Cone/Plate Rheometer ¹
Density (printed part)	1.2 g/cm ³	ASTM D792
Density (liquid resin)	1.11 g/cm ³	ASTM D4052-18a
Tensile Properties		
E Modulus	2600 MPa	ASTM D638
Ultimate Tensile Strength	62 MPa	ASTM D638
Elongation at Break	10 %	ASTM D638
Flexural Properties		
Flexural Modulus	2300 MPa	ASTM D790
Notched IZOD	108 MPa	ASTM D790
Impact Properties		
Notched Izod (Machined), 23 °C	21 J/m	ASTM D256
Unnotched Izod, 23 °C	112 J/m	ASTM D256
Charpy notched, 23 °C	1.3 kJ/m ²	ISO 179-1
Thermal Properties		
HDT at 0.45 MPa	87 °C	ASTM D648
HDT at 1.82 MPa	64 °C	ASTM D648
Flammability	HB	UL 94 1.5 mm
Hardness		
Shore D	83	ASTM D2240



Other

Biocompatibility	Information available on request	ISO 10993
Water Absorption, Short Term (24 hours)	0.42 %	ASTM D570

¹Determined with TA-Instrument DHR rheometer, cone/plate, diameter 60 mm, shear rate 100 s⁻¹

Disclaimer: The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. The safety data given in this publication is for information purposes only and does not constitute a legally binding MSDS. The relevant MSDS can be obtained upon request from your supplier or you may contact BASF 3D Printing Solutions GmbH directly at sales@basf-3dps.com.

About our Partner

At BASF, we create chemistry for a sustainable future. We combine economic success with environmental protection and social responsibility. Through science and innovation we enable our customers in nearly every industry to meet the current and future needs of society.

BASF 3D Printing Solutions GmbH
Speyerer Str. 4
69115 Heidelberg, Germany

Phone: +49 6221 67417 900
E-mail: sales@basf-3dps.com
Website: www.forward-am.com

